




IRON STRONG

DUCTILE IRON PIPE  
**TYTON<sup>®</sup>**  
**JOINT PIPE**  
 30"-36"




PIPE SIZE IN.	PIPE THICKNESS IN.		NOMINAL OUTSIDE DIAMETER	*DIMENSIONS IN.	
	FROM	TO	IN.	A	B
30	.34	.63	32.00	35.40	6.55
36	.38	.73	38.30	41.84	7.00

\* Nominal laying length is 18 feet.

**ASSEMBLY INSTRUCTIONS**

- STEP 1.** Thoroughly clean out the bell with special attention to the gasket recess. Remove any foreign material or excess paint. Clean the spigot or beveled plain end and remove any sharp edges with a standard file.
- STEP 2.** After making sure that the correct gasket is being used, insert it into the recess in the bell with the small end of the gasket facing the bell face.
- STEP 3.** Apply lubricant to the inside surface of the gasket, making sure that the entire surface is coated. Apply a generous coating of lubricant to the beveled portion of the plain end.
- STEP 4.** Guide the plain end into the bell, and while maintaining straight alignment, push the plain end into the bell socket. Once the joint is assembled, necessary deflection can be accomplished.



**PUSH-ON JOINT PIPE**

**MAXIMUM ALLOWABLE JOINT DEFLECTION**

PIPE SIZE IN.	Y-MAXIMUM JOINT DEFLECTION IN DEGREES	X DEFLECTION IN INCHES 18 FT. LENGTH	APPROXIMATE RADIUS IN FT. OF CURVE PRODUCED BY SUCCESSION OF JOINTS 18 FT. LENGTH
30	5°	19	206
36	5°	19	206

## DIMENSIONS AND WEIGHTS FOR SPECIAL CLASSES OF PUSH-ON DUCTILE IRON PIPE

PIPE SIZE IN.	THICKNESS CLASS	NOMINAL THICKNESS IN.	OD* IN.	WT. OF BARREL PER FT. † LB.	TYTON® JOINT		
					WT. OF BELL LB.	WT. PER LGTH. ‡ LB.	AVG. WT. PER FT. † LB.
30	50	0.39	32.00	118.5	139	2270	126.2
30	51	0.43	32.00	130.5	139	2490	138.2
30	52	0.47	32.00	142.5	139	2705	150.2
30	53	0.51	32.00	154.4	139	2920	162.1
30	54	0.55	32.00	166.3	139	3130	174.0
30	55	0.59	32.00	178.2	139	3345	185.9
30	56	0.63	32.00	190.0	139	3560	197.7
36	50	0.43	38.30	156.5	184	3000	166.7
36	51	0.48	38.30	174.5	184	3325	184.7
36	52	0.53	38.30	192.4	184	3645	202.6
36	53	0.58	38.30	210.3	184	3970	220.5
36	54	0.63	38.30	228.1	184	4290	238.3
36	55	0.68	38.30	245.9	184	4610	256.1
36	56	0.73	38.30	263.7	184	4930	273.9

## STANDARD DIMENSIONS AND WEIGHTS OF 30" THROUGH 36" PUSH-ON JOINT DUCTILE IRON PIPE

PIPE SIZE IN.	PRESSURE CLASS PSI	NOMINAL THICKNESS IN.	OD* IN.	WT. OF BARREL PER FT. † LB.	TYTON® JOINT		
					WT. OF BELL LB.	WT. PER LGTH. ‡ LB.	AVG. WT. PER FT. † LB.
30**	150	0.34	32.00	103.50	139.00	2000	111.20
	200	0.38	32.00	115.50	139.00	2220	123.20
	250	0.42	32.00	127.50	139.00	2435	135.20
	300	0.45	32.00	136.50	139.00	2595	144.20
	350	0.49	32.00	148.40	139.00	2810	156.10
36**	150	0.38	38.30	138.50	184.00	2675	148.70
	200	0.42	38.30	152.90	184.00	2935	163.10
	250	0.47	38.30	170.90	184.00	3260	181.10
	300	0.51	38.30	185.30	184.00	3520	195.50
	350	0.56	38.30	203.20	184.00	3840	213.40

† Including bell; calculated weight of pipe rounded off to the nearest 5 lb.

‡ Including bell; average weight per foot, based on calculated weight of pipe before rounding.

\* Tolerances of OD of spigot end: 30 – 36 in. = +0.08 in. & -0.06 in.

\*\* Fastite® Joint

## STANDARDS APPLICABLE TO DUCTILE IRON PIPE AND FITTINGS

<b>THICKNESS DESIGN OF DUCTILE IRON PIPE</b>	ANSI/AWWA C150/A21.50
<b>DUCTILE IRON PIPE FOR WATER AND OTHER LIQUIDS</b>	ANSI/AWWA C151/A21.51, FEDERAL WWP421D, GRADE C
<b>DUCTILE IRON PIPE FOR GRAVITY FLOW SERVICE</b>	ANSI/ASTM A746
<b>DUCTILE IRON FITTINGS FOR WATER AND OTHER LIQUIDS (3 in. through 36 in.)</b>	ANSI/AWWA C110/A21.10
<b>DUCTILE IRON COMPACT FITTINGS (3 in. through 24 in.)</b>	ANSI/AWWA C153/A21.53
<b>FLANGED FITTINGS</b>	ANSI/AWWA C110/A21.10, ANSI B16.1
<b>DUCTILE IRON PIPE WITH THREADED FLANGES</b>	ANSI/AWWA C115/21.15
<b>COATINGS AND LININGS</b>	
Asphaltic	ANSI/AWWA C151/A21.51, ANSI/AWWA C110/A21.10, ANSI/AWWA C153/A21.53
Cement Lining	ANSI/AWWA C104/A21.4
Various Epoxy Linings and Coatings	MANUFACTURER'S STANDARD
Exterior Polyethylene Encasement	ANSI/AWWA C105/A21.5
<b>JOINTS - PIPE AND FITTINGS</b>	
Push-On and Mechanical Rubber-Gasket Joints	ANSI/AWWA C111/A21.11, FEDERAL WWP421D
Flanged	ANSI/AWWA C115/A21.15, ANSI B16.1
Grooved and Shouldered	ANSI/AWWA C606
<b>PIPE THREADS</b>	ANSI B2.1
<b>INSTALLATION</b>	ANSI/AWWA C600

Tyton® and Tyton Joint® are registered trademarks of US Pipe and Foundry.



**POCKET ENGINEER**

Available for iOS + Android  
or online at [pe.mcwane.com](http://pe.mcwane.com)

CONNECT WITH US ON



**NEW JERSEY**

183 Sitgreaves St.  
Phillipsburg, NJ 08865  
908-454-1161

**OHIO**

2266 S. 6th St.  
Coshocton, OH 43812  
740-622-6651

**UTAH**

1401 E. 2000 South  
Provo, UT 84606  
801-373-6910



**CANADA**

Suite 1, 55 Frid Street,  
Hamilton, Ontario, Canada  
L8P 4M3