


IRON STRONG


TYTON® JOINT PIPE



	PIPE THICKNESS IN.		NOMINAL OUTSIDE DIAMETER	*DIMENSIONS IN.	
PIPE SIZE IN.	FROM	ТО	IN.	A	В
30	.34	.63	32.00	35.40	6.55
36	.38	.73	38.30	41.84	7.00
* Nominal laying length is 18 feet.					

ASSEMBLY INSTRUCTIONS

- **STEP 1.** Thoroughly clean out the bell with special attention to the gasket recess. Remove any foreign material or excess paint. Clean the spigot or beveled plain end and remove any sharp edges with a standard file.
- STEP 2. After making sure that the correct gasket is being used, insert it into the recess in the bell with the small end of the gasket facing the bell face.
- **STEP 3.** Apply lubricant to the inside surface of the gasket, making sure that the entire surface is coated. Apply a generous coating of lubricant to the beveled portion of the plain end.
- **STEP 4.** Guide the plain end into the bell, and while maintaining straight alignment, push the plain end into the bell socket. Once the joint is assembled, necessary deflection can be accomplished.



PUSH-ON JOINT PIPE

MAXIMUM ALLOWABLE JOINT DEFLECTION

PIPE SIZE IN.	Y-MAXIMUM JOINT DEFLECTION IN DEGREES	X DEFLECTION IN INCHES 18 FT. LENGTH	APPROXIMATE RADIUS IN FT. OF CURVE PRODUCED BY SUCCESSION OF JOINTS 18 FT. LENGTH
30	5°	19	206
36	5°	19	206

DIMENSIONS AND WEIGHTS FOR SPECIAL CLASSES OF PUSH-ON DUCTILE IRON PIPE

			WT. OF		TYTON* JOINT		
PIPE SIZE IN.	THICKNESS CLASS	NOMINAL THICKNESS IN.	OD*	BARREL PER FT.† LB.	WT. OF BELL LB.	WT. PER LGTH.† LB.	AVG. WT. PER FT.‡ LB.
30	50	0.39	32.00	118.5	139	2270	126.2
30	51	0.43	32.00	130.5	139	2490	138.2
30	52	0.47	32.00	142.5	139	2705	150.2
30	53	0.51	32.00	154.4	139	2920	162.1
30	54	0.55	32.00	166.3	139	3130	174.0
30	55	0.59	32.00	178.2	139	3345	185.9
30	56	0.63	32.00	190.0	139	3560	197.7
36	50	0.43	38.30	156.5	184	3000	166.7
36	51	0.48	38.30	174.5	184	3325	184.7
36	52	0.53	38.30	192.4	184	3645	202.6
36	53	0.58	38.30	210.3	184	3970	220.5
36	54	0.63	38.30	228.1	184	4290	238.3
36	55	0.68	38.30	245.9	184	4610	256.1
36	56	0.73	38.30	263.7	184	4930	273.9

STANDARD DIMENSIONS AND WEIGHTS OF **30" THROUGH 36" PUSH-ON JOINT DUCTILE IRON PIPE**

				WT. OF	TYTON* JOINT		
PIPE SIZE IN.	PRESSURE CLASS PSI	NOMINAL THICKNESS IN.	OD* IN.	BARREL PER FT. † LB.	WT. OF BELL LB.	WT. PER LGTH.† LB.	AVG. WT. PER FT.: LB.
	150	0.34	32.00	103.50	139.00	2000	111.20
30	200	0.38	32.00	115.50	139.00	2220	123.20
	250	0.42	32.00	127.50	139.00	2435	135.20
	300	0.45	32.00	136.50	139.00	2595	144.20
	350	0.49	32.00	148.40	139.00	2810	156.10
36	150	0.38	38.30	138.50	184.00	2675	148.70
	200	0.42	38.30	152.90	184.00	2935	163.10
	250	0.47	38.30	170.90	184.00	3260	181.10
	300	0.51	38.30	185.30	184.00	3520	195.50
	350	0.56	38.30	203.20	184.00	3840	213.40

- [†] Including bell; calculated weight of pipe rounded off to the nearest 5 lb.
- ‡ Including bell; average weight per foot, based on calculated weight of pipe before rounding.
- * Tolerances of OD of spigot end: 30 36 in. = +0.08 in. & -0.06 in.

STANDARDS APPLICABLE TO DUCTILE IRON PIPE AND FITTINGS

THICKNESS DESIGN OF DUCTILE IRON PIPE	ANSI/AWWA C150/A21.50			
DUCTILE IRON PIPE FOR WATER AND OTHER LIQUIDS	ANSI/AWWA C151/A21.51, FEDERAL WWP421D, GRADE C			
DUCTILE IRON PIPE FOR GRAVITY FLOW SERVICE	ANSI/ASTM A746			
DUCTILE IRON FITTINGS FOR WATER AND OTHER LIQUIDS (3 in. through 36 in.)	ANSI/AWWA C110/A21.10			
DUCTILE IRON COMPACT FITTINGS (3 in. through 24 in.)	ANSI/AWWA C153/A21.53			
FLANGED FITTINGS	ANSI/AWWA C110/A21.10, ANSI B16.1			
DUCTILE IRON PIPE WITH THREADED FLANGES	ANSI/AWWA C115/21.15			
COATINGS AND LININGS				
Asphaltic	ANSI/AWWA C151/A21.51, ANSI/AWWA C110/A21.10, ANSI/AWWA C153/A21.53			
Cement Lining	ANSI/AWWA C104/A21.4			
Various Epoxy Linings and Coatings	MANUFACTURER'S STANDARD			
Exterior Polyethylene Encasement	ANSI/AWWA C105/A21.5			
JOINTS - PIPE AND FITTINGS				
Push-On and Mechanical Rubber-Gasket Joints	ANSI/AWWA C111/A21.11, FEDERAL WWP421D			
Flanged	ANSI/AWWA C115/A21.15, ANSI B16.1			
Grooved and Shouldered	ANSI/AWWA C606			
PIPE THREADS	ANSI B2.1			
INSTALLATION	ANSI/AWWA C600			

Tyton® and Tyton Joint® are registered trademarks of US Pipe and Foundry.



CONNECT WITH US ON F In D









NEW JERSEY 183 Sitgreaves St. Phillipsburg, NJ 08865 908-454-1161

ОНЮ 2266 S. 6th St. Coshocton, OH 43812 740-622-6651

UTAH 1401 E. 2000 South Provo, UT 84606 801-373-6910



CANADA Suite 1, 55 Frid Street, Hamilton, Ontario, Canada L8P 4M3